

SERIE 2 300



Samples are representative. SPC is manufactured to truly represent wood in its unique character, design, colour and pattern. Please request further information if required.

SERIE 2 300



Samples are representative. SPC is manufactured to truly represent wood in its unique character, design, colour and pattern. Please request further information if required.

SERIE 2 300



DT420
BLACK



DT005
WHITE MARBLE



DT008
GREY MARBLE



DT015
BLACK MARBLE



Samples are representative. SPC is manufactured to truly represent wood in its unique character, design, colour and pattern. Please request further information if required.

SUBJECT	MAIN PARAMETER			REFERENCE
GENERAL INFORMATION				
Thickness	2mm			
Wear Layer	0.4mm / Class 32			
	Wood Design	Concrete Design	Marble Design	
Plank Size (mm)	228.6 x 1219.2	457.2 x 914.4	609.6 x 609.6	
Packaging	3.345m ²	5.20m ²	5.85m ²	
Planks per pack	12	14	14	
Application	Moderate Commercial			
TECHNICAL DATA				
Name	Regular Emboss (2mm/0.4mm)			
Type of flooring	Heterogeneous PVC floor covering			ISO 10582
Classification	32			ISO 10874
Component	PVC plasticizer Stabilizer CaCO ₃			
Structure	Composite (Wear Layer: 0.4mm; Print film: 0.07mm; Back Layer: 1.88mm)			
Size	Deviation ≤0.15% of nominal length up to 0.5mm maximum			ISO 24342
Squareness, mm	≤400mm deviation ≤0.25; >400mm, ≤0.35 >400mm, ≤0.35			ISO 24342
Straightness, mm	≤400mm deviation ≤0.25; >400mm, ≤0.35 >400mm, ≤0.35			ISO 24342
Overall thickness, mm	Average: 2.5mm + 0.13/-0.10mm, individual value: average +/- 0.15mm			ISO 24346
Wear layer thickness, mm	0.55mm +13%/ -10%			ISO 20340
Surface treatment	PU coating			
Bevelled edges	Painted V Groove			
Colour Fastness	Minimum 6			ISO 105-B02
Dimensional Stability	≤0.25%			ISO 23999
Total Mass Per Unit Area	4.286 kg/m ² + 13%/-10%			ISO 23997
Residual Indentation (average)	≤0.10 mm			ISO 24343-1
Reaction to fire	Bfl-s1			EN 13501-1
Chemical resistance	Class 0, excellent			ISO 26987
Effect of a castor chair	25 000 cycle no delamination			ISO 4918
Slip Resistance	≥R9			DIN 51130
	DS			EN 13893
Hardness	60°+/-5°			
Abrasion Resistance	Group T			EN660-2
Toxicity	Non-toxic, does not contain heavy metals			EN71-3
Formaldehyde Emission	E1			EN 717-1
Recycled Materials	No			
INSTALLATION & MAINTENANCE GUIDELINES				
Caution	Do not expose to direct sunlight			
Installation	Adhere to manufactures installation parameters			
Cleaning & Maintenance	Non-abrasive detergent & micro fibre mop			
	Avoid excessive exposure to water			